



OXIDISED BITUMEN

MEDIUM CURING STANDARD
GRADE CUTBACKS

PRODUCT DATA SHEET
EDITION 1, CUTBACK
BITUMEN

Characteristic	MC-30	MC-70	MC-3000
Kinematic Viscosity @ 140°F	30-60	70-140	3000-6000
Flash Point @ Cleveland open min F	100 min.	90-100°C	150 min.
Water Content	0.2%	0.2%	0.2%
Distillation (% total distillate to 680°F):-			
To 437°F	25%	20%	-
To 500°F	40-70%	20-60%	15%
To 600°F	75-93%	65-90%	15-75%
Residue (% Vol. from distillation to 680°F)	50% min.	55% min.	80% min.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of EMERALD BITUMEN's products, are given in good faith based on EMERALD BITUMEN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with EMERALD BITUMEN's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. EMERALD BITUMEN reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.