



CATIONIC BITUMEN EMULSION C40 BF6

PRODUCT DATA SHEET
EDITION 1, BITUMEN
EMULSION C40 BF6

C40 BF6 is a low-viscosity slow-set fluxed bitumen emulsion, commonly used for prime coats.

PROPERTIES	TEST METHOD	UNIT	C40 BF6 LIMITS
Breaking Value	ASTM D244	-	170-230
Recovered Binder Content (by distillation)	EN 12847	%	38-42
Efflux time 2mm at 40°C	EN 1429	S	15-45
Oil distillate content	EN 1431	%	5-15
Residue on sieving: 0.5mm sieve	EN 1431	% by mass	≤0.1
Residue on sieving: 0.16mm sieve –	-	% by mass	≤0.25
Residue on sieving: 7 days storage	EN1426	% by mass	≤0.2
Adhesion	EN13589	%	≤90
Penetration of recovered binder at 25°C	EN12592	0.1mm	≤300

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of EMERALD BITUMEN's products, are given in good faith based on EMERALD BITUMEN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with EMERALD BITUMEN's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. EMERALD BITUMEN reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.