



BITUMEN EMULSION EAR-1

PRODUCT DATA SHEET
EDITION 1, BITUMEN
EMULSION EAR-1

PROPERTIES	TEST METHOD	UNIT	EAR-1 LIMITS
Saybolt Viscosity: - Furol (25°C) - Furol (50°C)	ASTM D244	Sec. Sec.	20-100
Sedimentation (7 days)	EN 12847	%	< 5
Residue on sieving	EN 1429	%	< 0.1
Residual Bitumen	EN 1431	%	< 55
Water Content	EN 1428	%	< 45
Fluxing agent after distillation under 260°C	EN 1431	%	-
Particle charge	-	EN1430	Negative
Penetration (25°C, 100g, 5seg.)	EN1426	%	100-200
Ductility (5°C, 5cm/min.)	EN13589	%	< 40
Solubility	EN12592	%	< 97.5

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of EMERALD BITUMEN's products, are given in good faith based on EMERALD BITUMEN's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with EMERALD BITUMEN's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. EMERALD BITUMEN reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.